



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification 7 : G02F 1/1335, 1/1335, 1/19, 1/15</p>	<p>A2</p>	<p>(11) International Publication Number: WO 00/63745</p> <p>(43) International Publication Date: 26 October 2000 (26.10.00)</p>
<p>(21) International Application Number: PCT/EP00/03269</p> <p>(22) International Filing Date: 12 April 2000 (12.04.00)</p> <p>(30) Priority Data: 99201213.8 20 April 1999 (20.04.99) EP</p> <p>(71) Applicant: KONINKLIJKE PHILIPS ELECTRONICS N.V. [NL/NL]; Groenewoudseweg 1, NL-5621 BA Eindhoven (NL).</p> <p>(72) Inventors: CORNELISSEN, Hugo, J.; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). OUWERKERK, Martin; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). DUINE, Peter, A.; Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).</p> <p>(74) Agent: RAAP, Adriaan, Y.; Internationaal Octrooibureau B.V., Prof Holstlaan 6, NL-5656 AA Eindhoven (NL).</p>		<p>(81) Designated States: CN, JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published Without international search report and to be republished upon receipt of that report.</p>
<p>(54) Title: TRANSFLECTIVE DISPLAY DEVICE</p> <p>(57) Abstract</p> <p>Transflective display device having a translector (10) which is switchable between a transparent state and a mirror-like state. Preferably, a metal hydride optical switch is used as the translector.</p> <div data-bbox="533 730 854 1177"> </div>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NR	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Transflective display device.

The invention relates to a transflective display device comprising an electro-optical material between a first transparent substrate and a second transparent substrate, with an illumination device on the side of the second substrate.

Such display devices, notably liquid crystal display devices, find an
5 increasingly wider application in, for example, portable telephones, automotive uses, etc.

A transflective display device usually comprises a translector which, when used in transmission (referred to as the "night view mode") partly transmits light from a
10 backlight placed behind the display device or, when used in reflection (referred to as the "daytime view mode") reflects incident light.

In the common transfectors, the reflection is approximately 65% of the incident light, while only approximately 35% of the light from the backlight is passed by the translector. This is at the expense of the brightness, unless a brighter light source is chosen,
15 which requires extra energy and reduces the lifetime of the battery. An increase of the transmission in the "night view mode" is at the expense of brightness and contrast in the "daytime view mode".

20 It is, inter alia, an object of the invention to find a solution to the above-mentioned problem. To this end, a transflective display device according to the invention is characterized in that a switchable mirror is arranged between the illumination device and the electro-optical material, which mirror is switchable between a transparent state and a state reflecting light in the direction of the layer of electro-optical material.

25 A first embodiment of a transflective display device according to the invention is characterized in that the mirror is provided with a switchable layer comprising a trivalent metal which can form a hydride with hydrogen, and the switchable layer is reversibly switchable between a reflecting state and a transparent state by exchange of hydrogen.

The switchable layer preferably also comprises magnesium which can form hydrides. It has been found that a reflection of at least 75% and, in some cases, of 85% to 90% is realized with such layers, while these layers are switchable (within 1 to 10 sec) to a transparent state in which 80% to 90% of the light is transmitted. If necessary, the switchable layer is provided with a catalytically active layer comprising at least one metal of the group of palladium, platinum, cobalt and nickel.

A second embodiment of a transreflective display device according to the invention is characterized in that the switchable layer is in contact with a liquid electrolyte, a gel electrolyte or a solid-state electrolyte. Examples are 1 molar KOH in water, 1 molar trifluoroacetic acid in symmetric collidine and cerium oxide (CeO_2).

A particularly advantageous embodiment causes the switchable mirror and the illumination device to switch in a coupled way (for example, simultaneously).

These and other aspects of the invention are apparent from and will be elucidated with reference to the embodiments described hereinafter.

In the drawing:

Figs. 1 and 2 show a display device according to the invention in different states, while

Fig. 3 shows a variant of the switchable layer.

The Figures are diagrammatic and not drawn to scale; corresponding components are generally denoted by the same reference numerals.

Figs. 1 and 2 are diagrammatic cross-sections of a part of a display device, a liquid crystal display device in this embodiment, comprising a liquid crystal cell 1 with, in this embodiment, a twisted nematic liquid crystal material 2 which is present between two transparent substrates 3, 4 of, for example, glass, provided with electrodes (not shown). The device further comprises polarizers 5, 6 whose direction of polarization is, for example, mutually crossed perpendicularly. The device also comprises orientation layers (not shown) which orient the liquid crystal material on the inner walls of the substrates, in this embodiment in such a way that the cell has a twist angle of 90 degrees. In this case, the liquid crystal material has a positive optical anisotropy and a positive dielectric anisotropy. The cell 1 is bounded by a cell wall (not shown) or sealing edge.

Transparent electrodes (likewise not shown) of, for example, ITO (indium tin oxide) which cross each other in this embodiment and define pixels at the area of the crossings must be supplied with drive voltages. In the embodiment of Fig. 1, the electrodes are supplied with drive voltages by means of a drive circuit 12 via drive lines 7, 7' shown

diagrammatically. The device of Fig. 1 also comprises an illumination source 11 which is driven by the drive circuit 12 via drive lines 8, 8' shown diagrammatically.

According to the invention, the switchable mirror 10 is present between the illumination source 11 and the liquid crystal cell 1. In its simplest embodiment, the mirror 10 comprises a transparent substrate 20 of, for example, quartz glass, a switchable layer 21 of one of the metals Y or Gd, in this embodiment Gd, which in turn is coated with a thin palladium layer 22 (of approximately 5 nm). Such a switchable layer is described in greater detail in US 5,652,433. As described in this patent, the layer (GdH₂) has a mirror-like surface after manufacture and is not transparent. Incident light 23 (Fig. 2) which is passed by the display device 1 is reflected on the mirror 10 and observed by a viewer 24. When exposing the layer 21 to hydrogen, it changes into a light-transmissive layer (GdH₃). Light beams 25 from the illumination source 11 now pass the mirror 10 and reach the viewer 24. Said passage is reversible by exchange of hydrogen.

Atomic hydrogen may be added to the layer 21 in various manners, for example, from the gas phase or by means of electrochemical generation. However, use is preferably made of an electrically switchable layer. In this embodiment, the illumination source 11 is switched on via drive lines 8 simultaneously when the mirror is rendered transparent via drive lines 9. Simultaneously when the mirror is made non-transparent via drive lines 9, 9', the illumination source 11 is switched off via drive lines 8, 8'.

Such an electrically switchable mirror 10 is shown in Fig. 3. It comprises a transparent (glass) substrate 20, a first electrode of Gd_{0.4}Mg_{0.6}H_x (0.8 < x < 2.4) as a switching layer 21 having a thickness of about 200 nm (in this embodiment), a palladium layer 22 having a thickness of about 5 nm (in this embodiment), a thick layer 26 of a solid-state electrolyte Ta₂O₅·nH₂O, a second electrode 27 of transparent H_xWO₃ (0 < x < 0.5) having a thickness of about 350 nm (in this embodiment), and a conducting transparent ITO layer 28. All layers are transparent, while layer 21 is switchable between a reflecting state and a transparent state.

The stack of layers in Fig. 3 functions as follows. The layers 21 and 28 are connected to an external current source (for example, incorporated in the drive unit 12). By using a cathodic DC current on the first electrode 21, the low-hydrogen containing, mirror-like composition is converted into a transparent high-hydrogen containing composition. H_xWO₃ of

the second electrode 27 is then simultaneously converted into transparent WO_3 . The mirror 10 is now transparent. When reversing the current, the first state is reached again. Switching times are of the order of 1 to 10 sec for switching to the transparent state. Switching to the reflective state takes longer but is sufficiently rapid for the customary applications.

5 For a further description of other embodiments of the mirror of Fig. 3 and materials suitable for this mirror (for example, the use of platinum, cobalt or nickel instead of palladium, several suitable hydrogen conductors, materials for the switchable layer, etc.) reference is made to patent application PCT-WO 98/10329 (PHN 15.969).

10 In a display device as shown in Fig. 1, 2, with a mirror as shown in Fig. 3, reflection values of 80 to 90% were reached. The mirror has a transmission of at least 40% but this may increase to 80 to 90%, notably when the palladium layer is omitted.

The invention is of course not limited to the embodiments shown. As described, various other materials are possible for the switchable mirror such as a liquid electrolyte (for example, 1 molar KOH in water), a gel electrolyte (for example, 1 molar trifluoroacetic acid in
15 symmetric collidine) or a solid-state electrolyte (for example, cerium oxide (CeO_2)). Also completely different switching mechanisms than those with a current source are not excluded. Moreover, mirrors are feasible which do not switch in accordance with the mechanism of hydrogen exchange, for example, a switchable tin layer. Instead of a liquid crystal effect, a different electro-optical effect such as an electrophoretic effect may be used for the display
20 device.

In summary, the invention relates to a display device of the transfective type, in which the translector comprises a layer which is switchable between a transmissive and a reflective state.

The invention resides in each and every novel characteristic feature and each
25 and every novel combination of characteristic features.

CLAIMS:

1. A transfective display device comprising an electro-optical material between a first transparent substrate and a second transparent substrate, with an illumination device on the side of the second substrate, characterized in that a switchable mirror is arranged between the illumination device and the electro-optical material, which mirror is switchable between a
5 transparent state and a state reflecting light in the direction of the electro-optical material.
2. A transfective display device as claimed in claim 1, characterized in that the switchable mirror in the transparent state transmits at least 40% of the light.
- 10 3. A transfective display device as claimed in claim 1, characterized in that the switchable mirror is provided with a switchable layer comprising a trivalent metal which can form a hydride with hydrogen, and the layer is reversibly switchable between a reflecting state and a transparent state by exchange of hydrogen.
- 15 4. A transfective display device as claimed in claim 3, characterized in that the switchable layer also comprises magnesium.
5. A transfective display device as claimed in claim 4, characterized in that the switchable mirror in the transparent state transmits at least 65% of the light.
- 20 6. A transfective display device as claimed in claim 3, characterized in that the switchable layer is provided with a catalytically active layer comprising at least one metal of the group of palladium, platinum, cobalt and nickel.
- 25 7. A transfective display device as claimed in claim 1, characterized in that the electro-optical material comprises liquid crystalline material.

8. A transfective display device as claimed in claim 1, characterized in that the display device and the illumination device comprise means for coupling the switching of the switchable layer with the switching of the illumination device.

1/1




FIG. 1




FIG. 2




FIG. 3